



Middle Tg / CAF Resistance / Halogen Free EM-370(5) / EM-37B(5)

- Superior thermal resistance for lead-free process
- Excellent CAF resistance
- Halogen, antimony and red phosphorus free
- For LCD, memory module, mobile device and automotive applications

Basic Laminate Property

Property	Item		IPC-TM-650	Test Condition	Unit	Typical Value
Thermal	Tg		2.4.25	DSC	°C	155
			2.4.24	TMA	°C	150
			2.4.24.4	DMA	°C	175
	CTE, X/Y-axis		2.4.24.5	< Tg, TMA	ppm/°C	12/15
	CTE, Z-axis		2.4.24	< Tg, TMA	ppm/°C	35~40
				> Tg, TMA	ppm/°C	180~200
	Z-axis Expansion		2.4.24	50~260°C	%	2.6
	Td		2.4.24.6	TGA (5% W.L)	°C	385
T288		2.4.24.1	Clad	Min.	>60	
			Etched	Min.	>60	
Electrical	Dk (R/C: 50%)	1 MHz	2.5.5.9	C-24/23/50	-	4.8
		1 GHz			-	4.3
	Df (R/C: 50%)	1 MHz	2.5.5.9	C-24/23/50	-	0.009
		1 GHz			-	0.013
	Volume Resistivity		2.5.17.1	C-96/35/90	MΩ-cm	>10 ¹⁰
	Surface Resistivity		2.5.17.1	C-96/35/90	MΩ	>10 ⁹
CTI		UL-746A	ASTM D3638	PLC	3	
Physical	Water Absorption		2.6.2.1	E-1/105+D-24/23	%	0.13
	Peel Strength (HTE)	0.5 oz	2.4.8	As Received	lb/in	7.5
				After Thermal Stress	lb/in	7.5
		1.0 oz	2.4.8	As Received	lb/in	8.5
				After Thermal Stress	lb/in	8.5
	Flexural Strength	Warp	2.4.4	As Received	MPa	510~570
Fill		As Received		MPa	450~500	
Flame Resistance		UL-94	A & E-24/125	-	V-0	